

Dulux Wash&Wear +Plus Super Tough Low Sheen

AU_DD02077

Part A	N95-78310
---------------	-----------

Description

Wash&Wear +PLUS Super Tough is a two-pack epoxy paint that provides ultimate abrasion resistance to walls that need extra protection. The unique two-pack epoxy paint that forms a tough and hard wearing paint film. Wash&Wear +Plus Super Tough looks like ordinary low sheen paint, but it offers extraordinary performance for walls that need extra protection. Wash&Wear +Plus Super Tough can be repeatedly scrubbed so it will stay looking freshly painted for years.

- Features**
- Mix Part A and Part B to activate. Must be used within 48 hours of mixing.
 - Apply with brush, roller or spray
 - Creates a low sheen finish with a mild stipple that resembles normal Wash&Wear Low Sheen
 - Diamond Tough (TM) epoxy two pack
 - Hard wearing finish that lasts
 - Withstands wear & tear
 - Mark & stain resistant
 - Easy to keep clean

- Benefits**
- Ultimate scratch, scrape & scrub resistance
 - For walls that need extra protection
 - Offers complete washability: Stain resistance + Scrub Resistance + Burnish Resistance
 - Most common marks, scuffs and stains wipe off with a soft wet cloth.

Uses

For all interior walls that are subjected to harsh wear and tear.

Precautions And Limitations






Caution: Shake Part B thoroughly by hand, to homogenize, prior to mixing with Part A.

All preparation and painting must conform to AS2311: The Painting of Buildings. Do not use at temperatures below 10°C, or when the temperature of the surface may fall below 10°C during the drying period. Avoid exposure to steam and condensation for 48 hours after application. Although the film is dry to touch in 30 mins allow 7 days for film to fully cure before washing. The surface can be cleaned with a soft wet cloth. For more stubborn stains use a wet cloth and cleaner such as Ajax Spray n' Wipe.

Tinted Colours: Ensure that the paint is thoroughly shaken and stirred immediately after addition of tinter to the can and again before use.

Performance Guide

Weather	Designed for interior use only. Not recommended for exterior use.	Heat Resistance	Softens and sticks to other painted surfaces over 70°C
Solvent	Sensitive to aromatic hydrocarbons and alcohols.	Abrasion	Excellent wet and dry burnish resistance and stain removal

Typical Properties																											
Gloss Level	5 - 10 at 60°, 10-20 at 85°	Thinner	Water																								
Colour	Machine tinted to a wide range of colours from White base only																										
Dulux Colour Base	VIVID WHITE																										
Components	2	Number Of Coats	2																								
Toxicity	Lead free.	V.O.C. Level	<45g/L																								
Meets GBCA VOC Requirement?	No	Mixing Ratio	11:1																								
Pot Life	48 hours	Touch Dry	30 mins																								
Clean Up	 Water																										
Application Method	    Air Spray Airless Spray Brush Roller																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: right;">Solids By Volume</td> <td style="text-align: center;">40</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td style="text-align: right;">Wet Film Per Coat (microns)</td> <td style="text-align: center;">62.5</td> <td style="text-align: center;">62.5</td> <td style="text-align: center;">62.5</td> </tr> <tr> <td style="text-align: right;">Dry Film Per Coat (microns)</td> <td style="text-align: center;">25</td> <td style="text-align: center;">25</td> <td style="text-align: center;">25</td> </tr> <tr> <td style="text-align: right;">Recoat Time (min)</td> <td style="text-align: center;">120</td> <td style="text-align: center;">Indefinite</td> <td style="text-align: center;">120</td> </tr> <tr> <td style="text-align: right;">Theoretical Spread Rate (m²/L)</td> <td style="text-align: center;">16</td> <td style="text-align: center;">16</td> <td style="text-align: center;">16</td> </tr> </table>			Solids By Volume	40				Min	Max	Recommended	Wet Film Per Coat (microns)	62.5	62.5	62.5	Dry Film Per Coat (microns)	25	25	25	Recoat Time (min)	120	Indefinite	120	Theoretical Spread Rate (m ² /L)	16	16	16
Solids By Volume	40																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)	62.5	62.5	62.5																								
Dry Film Per Coat (microns)	25	25	25																								
Recoat Time (min)	120	Indefinite	120																								
Theoretical Spread Rate (m ² /L)	16	16	16																								

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> Previously painted Surfaces Wash down with sugar soap and rinse with clean water to remove any dirt, oil or grease. In cases where mould or mildew is present, use a household bleach solution. Dilute 1 part bleach with 3 parts clean water. Wear gloves and goggles. Use a scouring pad wet with bleach solution to lightly abrade the surface and ensure physical removal of stubborn areas of mould growth. Leave the bleach solution on the surface for 15 minutes, then thoroughly remove by washing down with clean water and wipe dry. In very severe cases, repeat this action to remove all mould. Scrape and sand any loose, peeling and flaking paint. Fill any cracks or holes with a suitable filler. Sand gloss and semi gloss finishes to a dull flat finish to allow a sound surface before top coating. dust off. Apply one coat of Dulux 1 Step Acrylic Primer, Sealer & Undercoat to any areas which have been repaired or which have an uneven gloss level. Bare Paperfaced Wallboard, Cement, Brick Brush down to remove any surface dust. Apply one coat of Dulux 1 Step Acrylic Primer, Sealer & Undercoat. Bare Interior Timber: Sand smooth. Dust off. Apply one coat of Dulux 1 Step Acrylic Primer, Sealer & Undercoat. Bare Set Plaster, Fibrous Plaster, Plasterglass: Brush down to remove any surface dust. Apply one coat of Dulux 1 Step Oil Based Primer, Sealer & Undercoat. For best results on bare set plaster and powdery surfaces apply one coat of Dulux Sealer Binder.
Application Procedure And Equipment	<ul style="list-style-type: none"> Pour Part B into Part A and mix thoroughly for 2 minutes with a broad flat paddle using an up and down scooping action. Apply two coats of Dulux Wash&Wear Plus Super Tough. Allow 2 hours between coats. Once mixed, product must be used within 48 hours. Brush/Roller: Use a medium nap roller. Pre-wet brushes and rollers with water before use. Avoid excessive brushing or rolling back into the paint which has been drying for more than 3 minutes. Remember using poor quality or worn rollers can affect the final finish achieved. Thinning: Not usually required. Under hot conditions application can be eased by thinning with up to 50mL of water per litre. Airless/Conventional Spray: Suitable for application by all standard spray equipment. For conventional spraying up to 100ml per litre of water may be added to aid atomisation. For airless spraying up to 30 ml per litre of water may be added to aid atomisation. <p>** Note: Some colours may require more than 2 coats, especially when painting over dark colours.</p>

Health And Safety			
MSDS Number	DLXGHSEN000956 DLXGHSEN000957	Protective Equipment	Wear eye protection and when spraying wear a dust mask.
In the case of emergency, please call 1800 033 111			

Transport And Storage			
Pack A	Wash&Wear Plus Super Tough Part A		
Size	Weight		
3.67L	5.0 kg		
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA
Size	Weight		
340mL	370g		
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427