

Dulux Enviro2 Interior Low Sheen

AU_DD02681

Part A	59L Line
---------------	----------

Description
Dulux Enviro2 Interior Low Sheen is a very low VOC, low odour premium water based paint. It produces a washable, stain resistance and hard wearing finish suitable for all interior living areas. It contains mould protection to help prevent mould growth.






Features
<ul style="list-style-type: none"> Water based premium acrylic paint Produces a hard wearing finish Washable and stain resistant

Benefits
<ul style="list-style-type: none"> Very low VOC <1g/L Low odour Helps prevent mould growth

Uses
Suitable for all interior living areas and Green Star, WELL, LBC building projects.

Precautions And Limitations
<p>All preparation and painting must conform to AS2311: The Painting of Buildings.</p> <p>Do not use at temperatures below 10°C, or when the temperature of surface may fall below 10°C during the drying period. Not recommended for application at temperatures higher than 28°C. Avoid exposure to steam and condensation for 48 hours after application. Although the film is touch dry in 30 minutes allow 7 days for film to fully cure before washing.</p> <p>Cleaning schedule: After application, allow the surface to dry for 7 days prior to cleaning. Do not scrub the surface, use abrasive cleaners or solvent. The surface should be wiped down with a soft damp cloth using mild detergent such as Spray & Wipe or similar.</p> <p>Darker colours will show more signs of marking and scuffing than lighter colours - if you are considering using a dark colour in a high traffic area you may want to consider a higher sheen level or the use of a protective clear coat.</p>

Performance Guide			
Weather	Designed for interior use only. Not recommended for exterior use.	Heat Resistance	Softens and sticks to other painted surfaces over 70°C
Water	Suitable for use in wet areas	Solvent	Sensitive to aromatic hydrocarbons and alcohols
Abrasion	Good wet and dry burnish resistance		

Typical Properties																											
Gloss Level	5-10 at 60 degrees, 5-15 at 85 degrees	Thinner	Water																								
Colour	White, may be tinted up to 56ml (2Y) per litre.	Components	1																								
Number Of Coats	2	Toxicity	Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.																								
V.O.C. Level	<1 g/L inclusive of Dulux low VOC tinter	Meets GBCA VOC Requirement?	Yes. Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.																								
Touch Dry	30 Minutes																										
Clean Up	 Water																										
Clean Up Description	Clean all equipment with water																										
Application Method	 Air Spray  Airless Spray  Brush  Roller																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">44</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td></td> <td></td> <td style="text-align: center;">61</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td></td> <td style="text-align: center;">27</td> </tr> <tr> <td>Recoat Time (min)</td> <td></td> <td></td> <td style="text-align: center;">2 hours</td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td></td> <td style="text-align: center;">16</td> </tr> </table>			Solids By Volume	44				Min	Max	Recommended	Wet Film Per Coat (microns)			61	Dry Film Per Coat (microns)			27	Recoat Time (min)			2 hours	Theoretical Spread Rate (m ² /L)			16
Solids By Volume	44																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)			61																								
Dry Film Per Coat (microns)			27																								
Recoat Time (min)			2 hours																								
Theoretical Spread Rate (m ² /L)			16																								

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> All surfaces must be prepared in accordance with proper trade practices and must be clean and free from dust, dirt, grease and oil. previously painted surfaces, except asbestos cement, must be sanded to remove loose, peeling, flaking or chalky paint. Spot prime bare areas. Note: To avoid dust from asbestos cement sheeting do not sand or scrub. Wash with bleach solution or appropriate de-mossing chemical where necessary. Wash down.
Application Procedure And Equipment	<ul style="list-style-type: none"> Brush, roller, spray Stir well before use with a broad, flat paddle using an up and down scooping action. Apply 2 coats of Dulux EnvirO2 Interior Low Sheen. Thin with up to 100ml of water per litre if necessary.

Health And Safety			
MSDS Number	DLXGHCEN003519	Health Effects	For detailed information refer to the product label and the current Material Safety Data Sheet available by calling Dulux Australia Toll free phone 13 23 77. Health effects: Splashes to the eye may cause eye irritation.
Protective Equipment	Personal Protective Equipment: Wear eye protection.		
In the case of emergency, please call 1800 033 111			

Transport And Storage			
Pack A	59L84179	Shipment Name	Not dangerous goods. No special transport requirements.
Size 4 Litre 10 Litre 15 Litre	Weight 6.0 Kg 14.8 Kg 21.9 Kg		
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.
 DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427